

Colour Fastness To Light
ISO 105 B02:2014: Method 2


white textile for
molo soft collection

molo design, ltd

1470 Venables Street
Vancouver, B.C.
Canada V5L 2G7

t +1 604 685 0340
f +1 604 685 0342

info@molodesign.com
www.molodesign.com



molo MATERIAL LIGHTFASTNESS	
COLOUR · MATERIAL	LIGHTFASTNESS LEVEL (BLUE WOOL SCALE)
white textile	8

LIGHTFASTNESS · OVERVIEW		
Lightfastness is a property of a colourant such as dye or pigment that describes its resistance to fading when exposed to light.		
LIGHTFASTNESS LEVEL (BLUE WOOL SCALE)	DIRECT EXPOSURE SUMMER / WINTER	NORMAL CONDITIONS OF DISPLAY*
1	-	less than 2 years
2	-	2-15 years
3	4-8 days / 2-4 weeks	2-15
4	2-3 weeks / 2-3 months	15-50 years
5	3-5 weeks / 4-5 months	15-50 years
6	6-8 weeks / 5-6 months	50-100 years
7	3-4 months / 7-9 years	over 100 years
8	over 1.5 years	over 100 years



Test Report

No. 1443366TX-01

Date: November 13, 2024

Page 1 of 3

MOLO DESIGN LTD
1470 Venables Street,
Vancouver, BC V5L 2G7
Canada

Attention: Coral Mercer

The following sample was submitted and identified by applicant as:

Sample Description	:	1070D White Textile
Buyer Name	:	Not Provided
Style No.	:	White Textile
Order No. / PO #	:	Not Provided
Color	:	White
Fiber Content	:	Non-Woven Polyethylene
Manufacturer	:	Not Provided
Country of Origin	:	Canada
Country of Destination	:	Not Provided
Applicant's submitted Care Instructions	:	Not Provided
Sample Receiving Date	:	October 22, 2024
Test Performance Period	:	October 23 – November 13, 2024
Tests Performed	:	Selected test(s) as requested by the applicant.
Test Results	:	Please refer to the following page(s).

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 30 days only.



Test Report

No. 1443366TX-01

Date: November 13, 2024

Page 2 of 3

Conclusions:

Test	Rating	Remarks
Colorfastness to Light	#	No Spec Provided; See Results.

Key:

- M = Meets specified or general requirement
- F = Fails to meet specified or general requirement
- S = Satisfactory
- U = Unsatisfactory
- # = No specified requirement

Signed for and on behalf of
SGS North America Inc.

Carlos Juarez
Manager – Textile Laboratory

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 30 days only.

Test Result(s):


Color Fastness To Light

ISO 105 B02:2014: Method 2

Grade (Bluewool Std)	8
----------------------	---

Remark: Rating in blue wool standard scale 1 -8, where 8 indicates the highest performance and 1 the lowest.

Sample Picture



Selected tests as requested by applicant against specified requirement / test request form / quotation.

*** End of Report ***

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 30 days only.